
DW212



Features:

DW212 combines glass fibre with increased temperature epoxy resin, processed by filament winding technology. The composite can be applied directly on the component or sleeves can produced which are pressed onto the rotor to achieve an interference fit. By minimizing of the gap between the rotor and stator and with regard to no eddy current losses the used material improves the performance and efficiency of high speed rotors.



Benefits:

Excellent chemical resistance

Low density – high strength

no eddy current losses

Improved performance and efficiency

Applications:

Fly wheels

Separating cans

Rotor reinforcement

Cyclic springs

Feasibility:

From Ø 10mm to Ø 1.500mm

Length up to 12.000mm

More dimensions upon request

TYPICAL PROPERTIES

Physical properties	Typical values	Units
Fibre	Glass	-
Matrix	Ероху	-
Color	variable	-
Density	2.10	g/cm ³
Mechanical properties		
Tensile strength	1.440	∥, MPa
E-modulus	53.000	∥, MPa
Max. elongation	2.7	 , %
Thermal properties		
Op. temp. continuous	-40 / +210	°C
Coeff. of expansion	8.5	, 10 ⁻⁶ 1/K

All data are approximate values